

(19) World Intellectual Property
Organization
International Bureau



(43) International Publication Date
25 August 2005 (25.08.2005)

PCT

(10) International Publication Number
WO 2005/077828 A1

(51) International Patent Classification⁷: **C01B 33/12**,
33/141, C09K 17/12, B09C 1/08

(21) International Application Number:
PCT/AU2005/000188

(22) International Filing Date: 14 February 2005 (14.02.2005)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
2004900702 13 February 2004 (13.02.2004) AU

(71) Applicant and

(72) Inventor: NUNN, Garry, Robert [AU/AU]; 150 Fisher
Road, Gympie, QLD 4570 (AU).

(74) Agents: INTELLEPRO et al.; Level 7, GPO Box 1339,
Brisbane QLD 4001 (AU).

(81) Designated States (unless otherwise indicated, for every
kind of national protection available): AE, AG, AL, AM,

AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN,
CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI,
GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE,
KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD,
MG, MK, MN, MW, MX, MZ, NA, NI, NO, NZ, OM, PG,
PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SY, TJ, TM,
TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM,
ZW.


(84) Designated States (unless otherwise indicated, for every
kind of regional protection available): ARIPO (BW, GH,
GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM,
ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM),
European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI,
FR, GB, GR, HU, IE, IS, IT, LT, LU, MC, NL, PL, PT, RO,
SE, SI, SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN,
GQ, GW, ML, MR, NE, SN, TD, TG).

Published:

— with international search report

For two-letter codes and other abbreviations, refer to the "Guid-
ance Notes on Codes and Abbreviations" appearing at the begin-
ning of each regular issue of the PCT Gazette.

(54) Title: SOLUBLE BIOGENIC SILICA AND APPLICATIONS USING SAME



(57) Abstract: A process of preparing a biogenic silica comprising the steps of incinerating a silica bearing organic source at a temperature up to 1200°C and allowing the incinerated silica organic source to cool; adding the incinerated and cooled silica bearing organic source to an alkaline solution that has either been preheated to a temperature up to about 65°C or to be heated with the added organic source to a temperature up to about 65°C, the alkaline solution being contained in a vessel and having a pH up to 14; applying heat so that the added organic source and the alkaline solution in the vessel are at a temperature between 100°C and up to about 300°C for 1 to 4 hours, thereby forming an aqueous biogenic silica and undissolved impurities derived from the added organic source; and extracting the aqueous biogenic silica from the vessel. The extracted silica can be solidified into a solid form.